

IN THE CLAIMS

Claim 1. (Original) A fiber mat for use in a building material, said mat comprising:

- a plurality of fibers;
- a resinous fiber binder, said fibers fixedly distributed in said binder; and
- a urethane modifier comprising from about 0.1 wt.% to about 50 wt.%, based on the weight of said binder.

Claim 2. (Original) The fiber mat of Claim 1, wherein said urethane modifier comprises a polyurethane modifier.

Claim 3. (Original) The fiber mat of Claim 2, wherein said polyurethane modifier is selected from the group consisting of: an aliphatic polyurethane, an aromatic polyurethane, and a hybrid polyurethane.

Claim 4. (Original) The fiber mat of Claim 1, wherein said fiber binder comprises a formaldehyde type binder.

Claim 5. (Original) The fiber mat of Claim 4, wherein said formaldehyde type binder is selected from the group consisting of: a urea/formaldehyde binder, a phenol/formaldehyde binder, and a melamine/formaldehyde binder.

Claim 6. (Original) The fiber mat of Claim 1, wherein the weight ratio of said fiber binder to said urethane modifier is in the range of from about 200:1 to about 4:1.

SERIAL NO. 10/789,215

Claim 7. (Original) The fiber mat of Claim 1, said mat containing from about 55 wt.% to about 98 wt.% fiber and from about 0.05 wt.% to about 45 wt.% fiber binder.

Claim 8. (Original) The fiber mat of Claim 1, wherein said fibers comprise glass fibers.

Claim 9. (Original) The fiber mat of Claim 1, said mat containing from about 55 wt.% to about 98 wt.% glass fiber and from about 15 wt.% to about 30 wt.% fiber binder.

Claim 10. (Original) The fiber mat of Claim 1, further comprising an asphalt coating on at least one surface of said mat, said mat having a tensile strength greater than about 1,000 psi.

Claim 11. (Original) A fibrous mat roofing shingle, comprising:
a plurality of glass fibers; and
a fixative composition comprising a fiber binder and between about 0.1 wt.% and about 50 wt.%, based on the weight of said binder, of a polyurethane modifier, wherein said fibers are fixedly distributed in said fixative composition.

Claim 12. (Original) The fibrous mat of Claim 11, wherein the concentration of the fiber binder, based on the weight of the fibrous mat, is in the range of from about 0.05 wt.% and about 45 wt.%.

Claim 13. (Original) The fibrous mat of Claim 11, wherein said glass fibers comprise a plurality of glass filaments having an average length of from about ¼ to about 3 inches and a diameter of from about 1 to about 50 microns.

SERIAL NO. 10/789,215

Claim 14. (Original) The fibrous mat of Claim 11, wherein the concentration of said glass filaments is between about 55 and about 98 wt.%.

Claim 15. (Original) The fibrous mat of Claim 11, wherein said polyurethane modifier is selected from the group consisting of: an aliphatic polyurethane, an aromatic polyurethane, and a hybrid polyurethane.

Claims 16 through 20. (Currently Cancelled)